

MIXING INSTRUCTIONS FOR LAST PATCH™ LIMESTONE


Quart Kit Contents:

- 1.72 lbs of "A" (in quart can)
- (4) tubes of "B"

Mixing Instructions: Last Patch™ Limestone is mixed 7 parts (by weight) of "A" side (thick sand-like mortar) to 1 part "B" side (clear watery). There are two different methods for achieving this mix ratio:

METHOD #1:


- 1) Take one cup and fill it until it reaches the 1 oz mark with part "A". (This gives you 49 grams of "A")
- 2) Take another cup and fill it with part "B" until it reaches the 1 tsp mark. (This gives you 7 grams of "B")
- 3) In a separate container combine both "A" and "B" from the above containers and thoroughly mix the material and immediately use.



METHOD #2:

- 1) Take the cup provided and fill to top with part "A" four times while emptying each cup into a separate mix container. (This gives you 196 grams of part "A")
- 2) Empty an entire tube of the "B" side into the container.
- 3) Thoroughly mix the material that was just measured out and immediately apply to repair area.

* Note: Add more part A if needed to get a "mortar-like" consistency



Mixing Tips:

- Product is a 7:1 ratio by Weight
- If desired you can add up to 10% of your own stone dust.
- Wear latex gloves to form the material around corners.
- Use powdered tints to adjust for variations in stone color.
- Apply the material as flush as possible on the surface of the stone before dry grinding, thus reducing grinding time.
- Mix to a mortar consistency.